



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/01/2014

TO: 20/01/2015

LAB. ID NUMBER: 33286
POWDER COATING: Glass-001
HEAT TRANSFER FILM: --
Colour variation (ΔE): 1,76
Residual gloss: 96%

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

**Unexposed area
(reference)**

**Exposed
area**

