

METALOOK SERIES

Bonded powder coatings with metal effects



Information:

1. [TECHNICAL INFORMATION](#)
2. [PRODUCTS AVAILABLE IN STOCK](#)
3. [MARKETING MATERIAL](#)

METALOOK

Bonded powder coatings with metal effects

1. TECHNICAL INFORMATION

• PRODUCT FEATURE

The powders of the *Metalook* series are characterized by extraordinary metal effects with special tonalities and shades; these very particular results are obtained with the bonding technology.

• TECHNICAL DATA

Chemical nature	Bonded Polyester			
Finish	Smooth glossy			
Product	Steelook-001	Titanlook-001	Goldlook-001	Silverlook-001
Class of resistance	Not for outdoor	Not for outdoor	Not for outdoor	For outdoor use
Yield in surface/mass	7,9 m ² /Kg			
Specific weight	1,27 ± 0,03 g/cm ³			

• APPLICATION AND CURING CYCLE

Available for corona charging.

Curing time and temperature:

- 20 minutes at 180°C – 356 F (metal temperature).
- 16 minutes at 190°C – 374 F (metal temperature).
- 12 minutes at 200°C – 392 F (metal temperature).

Recommended thickness: 80-90 micron.

• MECHANICAL PROPERTIES

Test	Standard Reference	Result
Buchholz	ISO 2815	ok
Cross-cut	ISO 2409	no loss of adhesion; ok
Impact 2,5 N*m	ISO 6272	ok
Bending	ISO 1519	no loss of adhesion; ok
Reverse impact test	ASTM D2794	ok

METALOOK

Bonded powder coatings with metal effects

2. PRODUCTS AVAILABLE IN STOCK

- PRODUCT CODE

STEELLOOK-001	GOLDLOOK-001
TITANLOOK-001	SILVERLOOK-001

- PACKAGING



Cardboard packaging; net weight 20 Kg – Lower weight miniboxes are available

3. MARKETING MATERIAL



A3 catalogue with aluminum samples

With each 20 kg product order will be delivered a copy **FOR FREE** of the **A3 catalogue with aluminum samples**.

On demand, it is possible to **customize the marketing material**.



GICOLOR SRL

Sede legale: Viale del Lavoro, 5 - 37040 Arcole (VR)

Sede operativa: Via Tagliamento, 4 - 36056 Belvedere di Tezze sul Brenta (VI)

Tel. +39 0424 560208 - Fax +39 0424 564601

